

Handling of ThermHex Honeycomb Cores

(abbreviated version)



Bonding of skin layer and honeycomb core:

During bonding of the ThermHex honeycomb core it is essential to use the right adhesive. The adhesive is significantly determined by the requirements of the sandwich compounds.



Laminating the skin layer onto the honeycomb core:

ThermHex honeycomb cores can be laminated with different methods for example hand lay-up with vacuum moulding, fiber resin spray-up, vacuum or light-rtm. Possible types of resin are polyurethane, polyester, epoxy or phenol.




Spray-up:

For large components or lamination of ThermHex honeycomb cores the fiber resin spray-up suits well. During this process, the merging of the compounds (resin, reactant and reinforcing fiber) as well as the deposition are done with a fiber-resin diffuser.



Forming:

Besides forming with heat it is also possible to form honeycomb cores of small thickness (e.g. 3.5 – 10mm) at room temperature during curing of the skin layers with the help of pressure or vacuum.



Cutting:

The cutting of ThermHex honeycomb cores is carried out with conventional tools and methods such as e.g. circular saw, circular knife, waterjet cutting, laser cutting, punching and so on.



Edge closure and load application:

Depending on the kind of procedure, usage and pressure on the finished sheet different edge closures are possible. For load application points, it is recommended to work with inserts that connect the two skin layers, in order to achieve a higher load application.

Liability for defects

All information provided herein is based on our current knowledge and experience. Due to the high number of possible influences during processing and application, the information does not release the processor from the necessity of carrying out his own investigations and tests. Information contained herein and explanations provided by ThermHex Waben GmbH in connection with this printed matter does not represent acceptance of a guarantee. Guarantee statements require special explicit written declarations on behalf of ThermHex Waben GmbH to be effective. The constitutions stated in this datasheet determine the properties of the delivery item extensively and conclusively.

Application suggestions do not establish assurance of suitability for the recommended application. We reserve the right to adapt the product to satisfy technical progress and new developments. We would be pleased to help with any enquiries including those related to special application issues. If the application for which our products are used is subject to statutory approval, the user is responsible for the procurement of such approval. Our recommendations do not release the user from the obligation of taking the possibility of impairments to third-party rights into account and of clarifying these if necessary. Furthermore we refer to our General Terms and Conditions, especially with regard to any possible liability for defects. If you are not in possession of our General Terms and Conditions we would be pleased to supply these on request.

THERMHEX WABEN GMBH

Merseburger Str. 237
D-06130 Halle/Saale

Tel.: +49 345 131627 10
Fax: +49 345 1316 27 19
Email: info@thermhhex.com
Web: www.thermhhex.com